

357-359, MESSOGION AVE., 15231 ATHENS, GREECE Tel.: 210 6501258

Fax: 210 6501551

TECHNICAL JOB SPECIFICATION

570/4

REVISION 0

DATE 05/04/2011

HIGH PRESSURE (HP) TRANSMISSION SYSTEMS

STUD - BOLTS AND NUTS



Job Spec. No Revision

570/4

Revisi Date 0 05-04-2011

Page

2/6

it is specially furnished

QUALITY ASSURANCE PAGE

CHANGES LOG

REVISIONS LOG

0	05-04-2011	FIRST ISSUE	PQ DPT	V.G.
Rev. No	Rev. Date	REASON FOR CHANGE	Made By	Approved By



Job Spec. No 570/4 Revision 0

Date

05-04-2011

Page

3/6

CONTENTS

REFERENCE DOCUMENTS

- 1.0 SCOPE
- 2.0 GENERAL REQUIREMENTS
- 3.0 TECHNICAL DOCUMENTATION
- 4.0 INSPECTION AND CERTIFICATION



Job Spec. No

570/4

Revision

05-04-2011

Date Page

4/6

0

REFERENCE DOCUMENTS

Job Spec. No. 970/2

[Shop Inspection of Equipment and Material for NGT Project]

ELOT EN 1515-1

[Flanges and their joints - Bolting - Part 1: Selection of bolting]

ELOT EN 1515-3

[Flanges and their joints. Bolting. Classification of bolt materials for steel flanges, class designated]

ELOT EN 1759-1 [Flanges and their joints. Circular flanges for pipes, valves, fittings and accessories, class-designated. Steel flanges, NPS 1/2 to 24]

ELOT EN 10045-1

[Charpy impact test on metallic materials; part 1: test method]

ELOT EN 10269

[Steels and nickel alloys for fasteners with specified elevated and/or low temperature properties]



Job Spec. No 570/4 Revision 0

Date

05-04-2011

Page

5/6

- 1.0 SCOPE
- 1.1 **ITEM**

Bolting materials for flanged joints.

1.2 SERVICE

Sweet natural gas with sporadic passage of water and glycol.

1.3 ADDITIONAL INFORMATION

Additional information may be given in the Material Requisition and should be read in conjunction with this material specification.

- 2.0 GENERAL REQUIREMENTS
- 2.1 **TYPE**

Stud bolts with 2 nuts as per ELOT EN 1515-1 and ELOT EN 1515-3, for flanges as per ELOT EN 1759-1.

- 2.2 MATERIAL
- 2.2.1 STUD BOLTS

Material 42CrMo4 as per ELOT EN 10269. See also table 1 of ELOT EN 1515-3.

2.2.2 NUTS

Material C45E as per ELOT EN 10269.

Nuts larger than 12 mm shall not be machined from barstock.

2.2.3 <u>IMPACT TESTS</u>

Stud bolts and nuts with thread diameter ≥50mm shall be Charpy V-notch impact tested in accordance with **ELOT EN 10045-1**. Test temperature shall be -20°C or lower.

- 2.3 DIMENSIONS
- 2.3.1 DIAMETER

As per Material Requisition

2.3.2 BOLT LENGTH

As per Material Requisition

2.3.3 THREAD

Fine thread as per ELOT EN 1515-1.

2.3.4 NUT

As per **ELOT EN 1515-1**.



Job Spec. No

570/4

Revision

0

Date Page 05-04-2011 6/6

2.4 MARKING

As per material standard.

2.5 SURFACE TREATMENT

Zinc (hot dipped galvanized) or phosphate coated.

2.6 PACKING

Bolts with nuts shall be packed separately by type, diameter and length. The packing shall be legibly marked with diameter and length.

3.0 TECHNICAL DOCUMENTATION

3.1 QUANTITY

Four copies of each, inclusive of original, for all documents and certificates. Also electronic files of all Documents and Certificates must be submitted by Contractor to the Owner.

3.2 DOCUMENT REQUIREMENTS

3.2.1 ON DELIVERY

Vendor's inspection certificate marked with Owner's supply contract number and containing as a minimum.

- Chemical analysis results.
- Tensile test results representative of the finished materials (studs only).
- Proof load test results representative of the finished materials (nuts only).
- Hardness test results representative of the finished materials (nuts only).
- Impact test results (thread diameter ≥ 50 mm only)

4.0 INSPECTION AND CERTIFICATION

Inspection requirements are defined in the following documents.

- a. Material requisition
- b. DESFA Job Specification No. 970/2 "Shop inspection of equipment and material for NGT project"
- c. Relevant project specifications
- d. Inspection clauses of applicable codes

Inspection procedures to be followed are detailed in Owner's document "Inspection and Test Instructions".